


PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : C07D 251/70, C08F 20/68</p>	<p>A1</p>	<p>(11) International Publication Number: WO 99/05127 (43) International Publication Date: 4 February 1999 (04.02.99)</p>
<p>(21) International Application Number: PCT/GB98/02104 (22) International Filing Date: 16 July 1998 (16.07.98) (30) Priority Data: 9715709.3 26 July 1997 (26.07.97) GB (71) Applicant (for all designated States except US): THE SECRETARY OF STATE FOR DEFENCE [GB/GB]; Defence Evaluation & Research Agency, Ively Road, Farnborough, Hampshire GU14 0LX (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): WILLIS, Colin, Robert [GB/GB]; CBD Porton Down, Salisbury, Wiltshire SP4 0JQ (GB). BREWER, Stuart, Anson [GB/GB]; CBD Porton Down, Salisbury, Wiltshire SP4 0JQ (GB). JONES, Brian, George [GB/GB]; CBD Porton Down, Salisbury, Wiltshire SP4 0JQ (GB). (74) Agent: BOWDERY, A., O.; D/IPR, Formalities Section, Poplar 2, MOD Abbey Wood #19, Bristol BS34 8JH (GB).</p>		<p>(81) Designated States: AU, CA, CN, GB, JP, KR, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published With international search report.</p>
<p>(54) Title: FLUORINATED TRIAZINE MONOMERS</p> <p>(57) Abstract</p> <p>A compound of formula (I), wherein R¹ and R² are independently selected from saturated fluorocarbon substituted side chains, such as NR⁵(CH₂)_nC_mF_{2m+1}, O(CH₂)_nC_mF_{2m+1}, S(CH₂)_nC_mF_{2m+1}, NR⁵S(O)₂(CH₂)_pC_mF_{2m+1}, or CR⁵[CO₂(CH₂)_nC_mF_{2m+1}]₂, where R⁵ is hydrogen or alkyl, n and m are independently an integer of 1-12, and p is 0 or an integer of 1-12, R³ is an unsaturated moiety which may be polymerised, and X is O, S or NR⁴ where R⁴ is hydrogen or alkyl, as well as methods for the preparation of these compounds. Compounds of formula (I) are useful monomers in the preparation of oil- and water-repellent polymers.</p> <div style="text-align: center;">  <p>(I)</p> </div>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

FLUORINATED TRIAZINE MONOMERS

The present invention relates to novel monomeric compounds which can be used in the production of polymers which have a high degree of oil and water-repellency and which may be fixed to substrates such as clothing, to processes for their preparation and to polymers produced therefrom.

Oil- and water- repellent treatments are in widespread use, in particular for outdoor clothing applications, sportswear, leisurewear and in military applications. These treatments generally require the incorporation of a fluoropolymer into or more particularly, fixed onto the surface of the clothing fabric. The degree of oil and water repellency is a function of the number of fluorocarbon groups or moieties that can be fitted into the available space. The greater the concentration of such moieties, the greater the repellency of the finish.


In addition however, the polymeric compounds must be able to form durable bonds with the substrate. Oil-and water-repellent textile treatments are generally based on fluoropolymers that are applied to fabric in the form of an aqueous emulsion. The fabric remains breathable and permeable to air since the treatment simply coats the fibres with a very thin, liquid-repellent film. In order to make these finishes durable, they are sometimes co-applied with cross-linking resins that bind the fluoropolymer treatment to fibres. Whilst good levels of durability towards laundering and dry-cleaning can be achieved in this way, the cross-linking resins can seriously damage cellulosic fibres and reduce the mechanical strength of the material.

WO 97/13024 discloses a group of fibre reactive polymers, which include a functional group such as a triazine group, which binds the polymer to the material substrate.

- 5 British patent No 1,102,903 describes certain fluoro alkyl containing compounds which are used in water- and oil-repellent compositions.

The applicants have produced certain novel monomers,
10 which give rise to polymers which have a high number of fluorocarbon substituents per monomer unit.

The present invention provides a compound of formula (I)



15

(I)

- wherein R¹ and R² are independently selected from saturated fluorocarbon substituted side chains;
20 R³ is an unsaturated moiety which may be polymerised, and X is O, S or NR⁴ where R⁴ is hydrogen or alkyl.

As used herein, the term "alkyl" refers to straight or branched chain alkyl or cycloalkyl groups, in particular
25 those having from 1 to 12 and preferably from 1 to 6 carbon atoms. The term "saturated" refers to groups which do not contain carbon-carbon double bonds. Conversely the term "unsaturated" refers to groups which include carbon-carbon double bonds.

30

Suitable fluorocarbon substituted side chains for R¹ and/or R² include groups which are hydrophobic groups

which are able to confer water- and/or oil- repellency on the resultant polymer. In particular R^1 and R^2 are independently selected from $NR^5(CH_2)_nC_mF_{2m+1}$, $O(CH_2)_nC_mF_{2m+1}$, $S(CH_2)_nC_mF_{2m+1}$, $NR^5S(O)_2(CH_2)_pC_mF_{2m+1}$ or

5 $CR^5[CO_2(CH_2)_nC_mF_{2m+1}]_2$, where R^5 is hydrogen or alkyl, and n and m are independently an integer of 1-12, and p is 0 or an integer of from 1-12.

Conveniently R^1 and R^2 are the same. They are preferably


10 selected from $O(CH_2)_nC_mF_{2m+1}$ or $NR^5S(O)_2(CH_2)_pC_mF_{2m+1}$. Suitably R^5 is methyl, ethyl or n-propyl, in particular ethyl. Preferred integers for n and p are from 1-3, suitably 2, whilst preferred integers for m are from 6 to 10, most preferably 8.

15 Suitable polymerisable groups R^3 are alkenes or alkynes which may also include a functional group such as an acyloxy group. Particularly preferred groups for R^3 are groups of formula $(CH_2)_qOC(O)C(R^6)CR^7R^8$ where q is an integer of from 1 to 12, suitably from 1 to 4 and

20 especially 2, and R^6 , R^7 and R^8 are independently selected from hydrogen or alkyl such as C_{1-4} alkyl. Preferably R^6 , R^7 and R^8 are all hydrogen.


Compounds of formula (I) are suitably prepared by

25 reacting a compound of formula (II)



(II)

30 where R^1 and R^2 are as defined in relation to formula (I) and Y is a leaving group, with a group of formula (III)



(III)

where X is as defined in relation to formula (I) and R^{3'}
5 is a group R³ as defined in relation to formula (I) or a precursor group which may be reacted to form a group R³ and R^a is hydrogen or alkyl; and thereafter if necessary converting a precursor group R^{3'} to a group R³.

10 Preferably R^a is hydrogen or a lower alkyl, for example a C₁₋₃ alkyl, in particular methyl.

Suitable leaving groups for Y include halogen such as fluorine and chlorine, in particular chlorine, or amine
15 leaving groups such as substituted pyridines for instance nicotinic acid or colladine.

The reaction is suitably effected in an organic solvent such as tetrahydrofuran (THF), acetone, toluene or
20 chloroform. It may be effected at temperatures of from 0 to 200°C, suitably from 25 to 150°C, depending upon the precise nature of the reactants and solvents involved. Conveniently the reaction may be effected at room temperature or under reflux conditions.


25 Preferably the reaction is effected under basic conditions. Weak bases may suffice, and in some instances, the compound of formula (III) may itself act as an acid scavenger and so the use of an excess,
30 particularly a 2 molar excess of the compound of formula (III) will ensure that that the reaction proceeds effectively.

Suitable groups R^{3'} which are precursor groups to R³ would
35 be apparent to the skilled person. For example, where R³ is a group (CH₂)_qOC(O)C(R⁶)CR⁷R⁸, a suitable precursor group R³ would be (CH₂)_qOH, which can be readily converted

to R^3 by reaction with a suitable acid halide for example an acid chloride of formula $ClC(O)C(R^6)CR^7R^8$ in the presence of a base, such as a weak base, for example pyridine or a pyridine derivative such as collidine.

- 5 This reaction is suitably effected in an organic solvent such as toluene at elevated temperatures, conveniently at the reflux temperature of the solvent.

Certain compounds of formula (II) are known (see for
10 example British Patent No. 1,102,903). These compounds can be prepared by reacting a compound of formula (IV)



(IV)

15

where R^1 is as defined in relation to formula (I), Y is as defined in relation to formula (II) and Y' is a leaving group,
with a compound of formula (V)

20



where R^2 is as defined in relation to formula (I), in the presence of a base.

25

Suitable bases are those which react with a compound of formula (V) so as to produce a nucleophilic moiety of formula (V')


30



Thus the selection of suitable bases will depend upon the precise nature of the group R^2 and will be readily understood or determinable by the skilled person. For example, where R^2 is a group $O(CH_2)_n C_m F_{2m+1}$, strong bases such as alkali metal hydroxides, in particular lithium hydroxide, may be used. Alternatively, where R^2 is a group $NR^5 S(O)_2 (CH_2)_p C_m F_{2m+1}$, stronger bases such as alkali metal alkoxides, in particular sodium or potassium methoxide or ethoxide may be used.

10

Compounds of formula (IV) are suitably prepared by reacting a compound of formula (VI)



15

(VI)

wherein Y, Y' and Y'' are the same or different leaving groups, with a compound of formula (VII)

20



where R^1 is as defined in relation to formula (I), in the presence of a base.

25

Reaction conditions will be generally similar to those described above in relation to the reaction between compounds of formula (IV) and formula (V).

30


Where compounds of formula (V) and formula (VII) are the same, compounds of formula (II) may be prepared directly in one pot. If necessary, the reaction can be controlled

in a stepwise manner in order to maximise yield of the target compound by controlling the reaction temperature. For example, where R^1 and R^2 are groups of formula $NR^3S(O)_2(CH_2)_nC_mF_{2m+1}$, the compound of formula (IV) may be prepared at depressed temperatures, for example at about -78°C . Allowing the reaction mixture to warm up to approximately 0°C will produce a compound of formula (II) after suitable work-up.

Compounds of formula (III), (V), (VI) and (VII) are either known compounds or they can be prepared from known compounds using conventional methods. A preferred compound of formula (VI) is cyanuric chloride.


Compounds of formula (I) may be polymerised or copolymerised using conventional technology, e.g emulsion polymerisation.

Polymers or copolymers including units of formula (VIII)



(VIII)

where R^1 , R^2 and X are as defined in relation to formula (I), t is an integer in excess of 5, and R^9 is a saturated derivative of R^3 as defined in relation to formula (I) form a preferred embodiment of the invention. In particular XR^9 will be a moiety of formula (IX)



(IX)

Suitably the monomers of the invention are copolymerised with a monomer which comprises a fibre reactive moiety
 5 for example as described in WO 97/13024.

The invention will now be particularly described by way of example.

10 Example 1

Step 1

Synthesis of 2-chloro-4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazine

Metallic sodium (4.08g, 177mmols) was reacted with
 15 methanol (150mls). N-Ethyl perfluorooctyl sulphonamide (93.28g, 177mmols) was added, and the resulting solution was stirred for 30 minutes. The methanol was removed at the pump (a vacuum pump was required to remove the final traces of solvent). The resulting sticky solid was
 20 dissolved in acetone (300mls) and cooled to -65°C under argon. Recrystallised cyanuric chloride (16.33g, 88.5mmols) dissolved in acetone (100mls) was added to the reaction mixture dropwise such that the temperature did not rise above -50°C (~1hour). After the addition, the
 25 reaction mixture was allowed to slowly warm to room temperature (1 hour) and then stirred for a further 3 hours. The precipitated solid was removed by filtration and dried under vacuum. Purification by soxhlet extraction with acetone afforded 61g (56.9%) of a fine white powder.

30

^1H NMR (CDCl_3) δ (ppm) 4.20 (2H, q, $^3\text{J}_{\text{H-H}}$ 6.8 Hz, CH_2CH_3), 1.40 (3H, t, $^3\text{J}_{\text{H-H}}$ 6.8 Hz, CH_2CH_3).

$^{13}\text{C}\{^1\text{H}\}$ NMR (CDCl_3) δ (ppm) 171.3, 165.0 (triazine), 46.3 (CH_2CH_3), 14.5 (CH_2CH_3).

5 Step 2

Synthesis of 2-N-(4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazin-2-yl)-amino ethanol

A THF solution (85mls) of 2-chloro-4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazine (15g, 12.9mmols) and ethanolamine (1.6g, 26.2mmols) were heated under reflux for 1 hour. The hot solution/suspension was filtered and the product was allowed to crystallise overnight to afford 12.8g (83%) of product.

15

^1H NMR (d_6 acetone) δ (ppm) 4.85 (4H, m, NCH_2CH_3), 4.38 (2H, t, $^3\text{J}_{\text{H-H}}$ 5 Hz, CH_2O), 4.22 (2H, dt, 5, 5 Hz, $\text{OCH}_2\text{CH}_2\text{N}$), 2.05 (6H, m NCH_2CH_3).

20 Step 3

Synthesis of 2-N-((4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazin-2-yl))-aminoethyl propenoate

2-N-[4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazin-2-yl]amino ethanol (11.58, 9.7mmols) and acryloyl chloride (1.32g, 14.6mmols) were dissolved in hot toluene (80mls). Collidine (1.77g, 14.6mmols) was added as a toluene solution (10mls) down the reflux condenser. The resulting reaction mixture was heated under reflux for 2 hours and then filtered hot. Toluene was removed at the pump and the resulting solid dissolved in diethyl ether (400mls). The ethereal solution was washed with 1M HCl (2x50mls) distilled water (2x40mls) and then dried over sodium sulphate. Filtration and evaporation of the solvent at the pump afforded 8.8g (73%) of product.

¹H NMR (CDCl₃) δ (ppm) 6.42 (1H, dd, ³J_{H-H} 17.3, 1.3 Hz, CH=CH₂ *trans*), 6.11 (1H, dd, ³J_{H-H} 17.3, 10.5 Hz, CH=CH₂), 5.88 (2H, m, NH, CH=CH₂ *cis*), 4.32 (2H, t, ³J_{H-H} 5.3 Hz, CH₂O), 4.13 (4H, m, NCH₂CH₃), 3.72 (2H, m, OCH₂CH₂N), 1.36 (6H, m, NCH₂CH₃).

¹³C{¹H} NMR (CDCl₃) δ (ppm) 166.0, 165.6, 164.6, 164.3, (triazine/C=O), 131.5 (C=C), 127.8 (C=C), 62.5 (CH₂O), 45.4 (CH₃CH₂N), 40.5 (CH₂N), 14.9 (CH₃CH₂).

Example 2

Synthesis of 2-[N-methyl-N-((4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazin-2-yl))]-aminoethyl propenoate

2-Chloro-4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazine (20g, 17.2mmols) was held as a solution/suspension in chloroform (150mls). N,N-Dimethylethylamino acrylate (2.45g, 17.2mmols) was added dropwise, over a period of 30 minutes, as a chloroform solution (50mls). The reaction mixture was stirred for 3 hours at room temperature. The chloroform solution was filtered through Celite®, concentrated (to a volume of approximately 30mls) and then passed through a short path column of silica. Product was eluted with chloroform. Evaporation of the solvent afforded 19g (88%) of a sticky oil that crystallised with time (2 days).

¹H NMR (CDCl₃) δ (ppm) 6.37 (1H, dd, ³J_{H-H} 17.3, 1.5 Hz, CH=CH₂ *trans*), 6.09 (1H, dd, ³J_{H-H} 17.3, 10.5 Hz, CH=CH₂), 5.83 (1H, dd, ³J_{H-H} 10.5, 1.5 Hz, CH=CH₂ *cis*), 4.36 (2H, t, ³J_{H-H} 5.6 Hz, CH₂O), 4.14 (4H, m, NCH₂CH₃), 3.86 (2H, t, ³J_{H-H} 5.6 Hz, OCH₂CH₂N), 3.20 (3H, s, CH₃N), 1.38 (6H, m, NCH₂CH₃).

$^{13}\text{C}\{^1\text{H}\}$ NMR (CDCl_3) δ (ppm) 165.8, 164.5, 164.2, 164.0, (triazine/ $\text{C}=\text{O}$), 131.3 ($\text{C}=\text{C}$), 127.9 ($\text{C}=\text{C}$), 61.7 (CH_2O), 48.3 (CH_2N), 45.5 (CH_2N), 36.3 (CH_3N), 15.0 (CH_3CH_2).

5 **Example 3**

Step 1

Synthesis of 2,4-Bis(1H,1H,2H,2H-perfluorooctoxy)-6-chloro-1,3,5-triazine

Lithium hydroxide (0.49g, 11.7mmols) and 1H,1H,2H,2H
10 perfluorooctanol (5.4g 11.7mmols) were held as a
solution/suspension in tetrahydrofuran (25mls). Cyanuric
chloride (1.08g, 5.8mmols) and distilled water (1ml) were
added and the reaction mixture was stirred at room
temperature overnight. The resulting solution/suspension
15 was precipitated into distilled water (200mls) and
extracted with diethyl ether (2x200mls). The organic
extract was dried over sodium sulphate, filtered and the
diethyl ether was removed at the pump. The resulting
white solid was recrystallised from diethyl ether (50mls),
20 to afford 3.3g (54%) of product.

^1H NMR (CDCl_3) δ (ppm) 4.75 (2H, t, $^3\text{J}_{\text{H-H}}$ 6.6 Hz, OCH_2CH_2),
2.63 (2H, tt, $^3\text{J}_{\text{H-F}}$ 18.1 Hz, $^3\text{J}_{\text{H-H}}$ 6.6 Hz OCH_2CH_2).

25 $^{13}\text{C}\{^1\text{H}\}$ NMR (CDCl_3) δ (ppm) 173.2, 171.7 (triazine), 61.1
(OCH_2CH_2), 30.5 (t, $^2\text{J}_{\text{C-F}}$ 22.0 Hz $\text{OCH}_2\text{CH}_2\text{CF}_2$).

Step 2

Synthesis of 2-[N-methyl-N-((4,6-bis(1H,1H,2H,2H-perfluorooctoxy)-1,3,5-triazin-2-yl))]-aminoethyl propenoate

2,4-Bis(1H,1H,2H,2H-perfluorooctoxy)-6-chloro-1,3,5-
triazine (0.5g, 0.48mmols) was held as a
solution/suspension in chloroform (10mls). N,N-
35 Dimethylethyl-amino acrylate (0.076g, 0.53mmols) was
added dropwise as a neat liquid at room temperature and
the reaction mixture was stirred for 2 hours. The

chloroform solution was extracted with 2M HCl (2x10mls), distilled water (2x10mls), dried over sodium sulphate and filtered. Evaporation of the solvent afforded 0.48g (90%) of product as a waxy solid.

5

^1H NMR (CDCl_3) δ (ppm) 6.30 (1H, d, $^3J_{\text{H-H}}$ 17.2 Hz, $\text{CH}=\text{CH}_2$ trans), 6.00 (1H, dd, $^3J_{\text{H-H}}$ 17.3, 10.4 Hz, $\text{CH}=\text{CH}_2$), 5.75 (1H, d, $^3J_{\text{H-H}}$ 10.4 Hz, $\text{CH}=\text{CH}_2$ cis), 4.57 (4H, m, $\text{CF}_2\text{CH}_2\text{CH}_2\text{O}$), 4.31 (2H, t, 5.5 Hz, $\text{OCH}_2\text{CH}_2\text{N}$), 3.84 (2H, t, $^3J_{\text{H-H}}$ 5.5 Hz, $\text{OCH}_2\text{CH}_2\text{N}$), 3.14 (3H, s, CH_3N), 2.56 (4H, m, $\text{CF}_2\text{CH}_2\text{CH}_2\text{O}$).

10


$^{13}\text{C}\{^1\text{H}\}$ NMR (CDCl_3) δ (ppm) 171.3, 171.1, 167.3, 165.8, (triazine/ $\text{C}=\text{O}$), 131.1 ($\text{C}=\text{C}$), 128.0 ($\text{C}=\text{C}$), 61.8 (CH_2O), 59.2 (CH_2N), 48.0 (CH_2N), 36.1 (CH_3N), 30.2 (t, 22 Hz, CH_2CF_2).

15

20

Claims

1. A compound of formula (I)



(I)

wherein R¹ and R² are independently selected from saturated fluorocarbon substituted side chains; R³ is an unsaturated moiety which may be polymerised, and X is O, S or NR⁴ where R⁴ is hydrogen or alkyl.

2. A compound according to claim 1 wherein R¹ and R² are independently selected from NR⁵(CH₂)_nC_mF_{2m+1}, O(CH₂)_nC_mF_{2m+1}, S(CH₂)_nC_mF_{2m+1}, NR⁵S(O)₂(CH₂)_pC_mF_{2m+1} or CR⁵[CO₂(CH₂)_nC_mF_{2m+1}]₂, where R⁵ is hydrogen or alkyl, n and m are independently an integer of 1-12, and p is 0 or an integer of from 1-12.


3. A compound according to claim 1 or claim 2 wherein R¹ and R² are the same.

4. A compound according to any one of the preceding claims wherein R¹ and R² are selected from O(CH₂)_nC_mF_{2m+1} or NR⁵S(O)_p(CH₂)_nC_mF_{2m+1} where n, m, p and R⁵ are as defined in claim 2.

5. A compound according to any one of the preceding claims R³ is a group of formula -(CH₂)_qOC(O)C(R⁶)CR⁷R⁸ where q is an integer of from 1 to 12, and R⁶, R⁷ and R⁸ are independently selected from hydrogen or alkyl such as C₁₋₄ alkyl.


6. A compound according to claim 5 where R^6 , R^7 and R^8 are all hydrogen.

7. A method of preparing a compound of formula (I) as defined in claim 1, which method comprises reacting a compound of formula (II)



(II)

where R^1 and R^2 are as defined in claim 1 and Y is a leaving group, with a group of formula (III)




(III)

where X is as defined in claim 1 and $R^{3'}$ is a group R^3 as defined in relation to formula (I) or a precursor group which may be reacted to form a group R^3 and R^a is hydrogen or a lower alkyl group; and thereafter if necessary converting a group $R^{3'}$ to a group R^3 .

8. A method according to claim 7 wherein $R^{3'}$ is a group of formula $(CH_2)_qOH$, and this is subsequently converted to R^3 by reaction with an acid halide of formula $ZC(O)C(R^6)CR^7R^8$ where Z is a halogen and R^6 , R^7 and R^8 are as defined in claim 5, in the presence of a base.

9. A process for preparing a compound of formula (II) as defined in claim 7 which comprises reacting a compound of formula (IV)




where R¹ is as defined in relation to formula (I), Y is as defined in relation to formula (II) and Y' is a leaving group, with a compound of formula (V)



where R² is as defined in relation to formula (I), in the presence of a base.

10. A method according to claim 9 wherein the compound of formula (IV) is prepared by reacting a compound of formula (VI)



wherein Y, Y' and Y'' are the same or different leaving groups, with a compound of formula (VII)




where R^1 is as defined in claim 1, in the presence of a base.

11. A method according to claim 10 wherein the compound of formula (IV) is converted to a compound of formula (II) in situ.

12. A polymeric compound which has been derived from a compound of formula (I).


13. A polymeric compound according to claim 12 which comprises a polymer or copolymer including repeating units of formula (VIII)



(VIII)

where R^1 , R^2 and X are as defined in relation to formula (I), t is an integer in excess of 5, and R^9 is a saturated derivative of R^3 as defined in relation to formula (I).

14. A polymeric compound according to claim 13 wherein XR^9 is a moiety of formula (IX)



(IX)

15. A substrate which is coated with a polymeric compound according to any one of claims 12 to 14.
16. A substrate according to claim 15 which is a fabric.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 98/02104

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C07D251/70 C08F20/68

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C07D C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 366 884 A (AMERICAN CYANAMID CO) 9 May 1990 see claims 3,8 ---	1, 12
A	WO 97 13024 A (SECR DEFENCE ; WILLIS COLIN ROBERT (GB); BREWER STUART ANSON (GB)) 10 April 1997 cited in the application see page 1; claims ---	1, 12, 16
A	GB 1 102 903 A (DAIKIN) 14 February 1968 cited in the application see claims 1,8 -----	1, 12

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

16 September 1998

Date of mailing of the international search report

24/09/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

De Jong, B

INTERNATIONAL SEARCH REPORT

Information on patent family members

In International Application No

PCT/GB 98/02104

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0366884 A	09-05-1990	US 5175201 A	29-12-1992
		AT 132493 T	15-01-1996
		CA 1339662 A	10-02-1998
		DE 68925339 D	15-02-1996
		DE 68925339 T	01-08-1996
		JP 2172980 A	04-07-1990
		MX 169828 B	27-07-1993
		NO 302829 B	27-04-1998
		US 5410051 A	25-04-1995
		US 5359014 A	25-10-1994
WO 9713024 A	10-04-1997	EP 0854951 A	29-07-1998
		GB 2318354 A	22-04-1998
GB 1102903 A		JP 48041152 B	05-12-1973
		CH 253565 A	
		CH 443875 B	
		DE 1494430 A	09-10-1969
		FR 1438617 A	29-07-1966